

Pigment Red 123 for Inks

High Performance Perylene Pigments Producer in China

Pigment Red 123 (Brilliant Red 123) is a high performance perylene pigments, which is widely used in printing inks, plastics, metallic paint and industrial paint, it has strong light fastness and heat resistance, and the color strength is also very hight.

Chemicals Product Trade Name Pigment Red 123 C.I. No. C.I.71145 CAS No. 24108-89-2 EC No. 246-018-4 Molecular Formula C₄₀H₂₆N₂O₆

Physical Data

Physical State	Powder
Appearance	Fuchsia powder or paste
Odor	Odorless
Molecular Weight	630.66
PH Value	6-7
Light Fastness	6-7
Heat Resistance	200℃
Strength %	100±5
Moisture %	\leq 0.5(powder); \leq 80%(paste)

Water Soluble Salts (%) <0.5


100.0				5.0	Diam µm	Percen
90.0				4.5	0.30	3.26
80.0				4.0	0.80	18.34
70.0	N			3.5	2.00	39.56
60.0	$-H \wedge \wedge$		/\	3.0 ₽.	10.00	62.94
60.0 50.0 40.0	1111		/ \	2.5	20.00	72.41
40.0		\	/	2.0 8	35.00	84.69
30.0		\sim		1.5	40.00	88.80
20.0			111111111111111111111111111111111111111	1.0	42.00	90.22
10.0		V	111	0.5	45.00	92.22
					50.00	94.86
0.0	1.0	10.0	100.0	0.0		
		Size(µm)				

Partical Size

ID	Pd	Pcd	P/Po	V	1/[V(Po/P-1)]
2	12.61506	6.45365	0.06294	7.29289	0.00921
3	16.17877	10.13507	0.09884	8.18365	0.01340
4	19.76278	13.77996	0.13439	9.06378	0.01713
5	22.84349	17.21379	0.16788	9.87981	0.02042
6	27.21086	21.00887	0.20489	10.74246	0.02399
7	30.98970	24.81205	0.24198	11.53297	0.02768
8	34.79289	28.60307	0.27895	12.38380	0.03124
9	38.58390	32.39408	0.31592	13.23462	0.03490
Slope	Intercept	Vm		С	Cc
0.10033	0.00336	9.6437	0	30.86071	0.99963

BET Surface Area (m2/g): 42.04653

Regulatory Compliance EN 71 (94/62/CE) Azodyes (2002/61/CE) Applications Pringting Ink Metallic Paint Automobile Paint Plastic recommended O limited suitability



鸿港化工

Liaoning HongGang Chemicals Co., Ltd

No.6, Wanhe 2 Road, Aromatics

Base, Liaoyang City, Liaoning Prov,

China

Tel:0419-7675988 Fax:0419-7675289

E-mail: Lyns3322@163.com Sales@liangangchem.com

www.liangangchem.com